# XR403 Molecular Sieve 5A

#### **Products Introduction:**

XR403 **Molecular sieve 5A** is an adsorbent used for desulphurization during nature gas purification process.

Specially developed molecular sieves can also be used in PSA oxygen generator and PSA hydrogen purification process.

XR403 Molecular sieve 5A is made by synthetic zeolite powder 5A with selected mineral binder. XR403 Molecular sieve 5A has an effective pore opening of 5Å (0.5nm), it can adsorb molecules which diameter less than 5Å (0.5nm), is mainly used for desulphurization during nature gas purification process.

#### Characteristics:

Istable and excellent static and kinetic adsorption capacity

Ihigher crush strength

Property	Unit	Bead		Pellet		Note
		8x12	4x8	1/16"	1/8"	Note
Static						
Water	%wt	≥ 21.50	≥ 21.50	≥ 21.50	≥ 21.50	RH50%, 25°C
Adsorption						
Crush	N	≥ 30.00	≥ 80.00	≥ 30.00	≥ 70.00	Avg. 25 beads
Strength						
Crush	lbs	≥ 7.00	≥ 18.00	≥ 7.00	≥ 16.00	Avg. 25 beads
Strength						
Bulk	g/ml	≥ 0.68	≥ 0.68	≥ 0.64	≥ 0.64	Settle
Density						
Bulk	lbs/ft <sup>3</sup>	≥ 42.00	≥ 42.00	≥ 40.00	≥ 40.00	Settled
Density	IDO/IL	2 42.00	£ 42.00	2 40.00	2 40.00	Gettied
Loss on	%wt	≤ 1.50	≤ 1.50	≤ 1.50	≤ 1.50	575℃, 1hr
Ignition	/0WL	= 1.00	= 1.50	<b>⊒</b> 1.30	= 1.50	575 C, 1111

Zibo XiangRun Environment Engineering Co., ltd

Phone:86-533-3037068 Fax: 86-533-3037068 Tel: 86-13518630890 13583393236

 $Website: \underline{Http://xradsorbent.com}; \ \underline{Http://www.aluminaadsorbents.com}$ 

international@xradsorbent.com; sales@aluminaadsorbents.com

Address: No.16, Hi-Tech Industrial Park, Development Zone, Zibo City, Shandong Province 255000, P. R. China

Email:

Loss on	0/ 14/4	< 0.10	< 0.10	< 0.20	< 0.20	
Attrition	%wt	≤ 0.10	≤ 0.10	≤ 0.30	≤ 0.30	~
Particle	0/	> 07 00	> 00 00			
Ratio	%	≥ 97.00	≥ 99.00	~	~	~

## Application:

- 1. Adsorb H2O, CO2, H2S from sour natural gas streams, while decreasing COS formation.
- 2. Separation of normal- and iso-paraffins.
- 3. Production of high purity N2, O2, H2 and inert gases from mixed gas streams.

## Storage:

lAvoid moisture, avoid scrolling, throw and sharp shocking during transportation, rainproof facilities should be readied..

Ilt should be stored in dry and ventilated warehouse to prevent contamination or moisture.

#### Packaging information:

Туре	Carton	Drum	Super sack	
Bead	25kg/ 55lb	140 kg/ 208 lb	1000kg/ 2200 lb	
Pellet	25kg/ 55lb	130 kg/ 286 lb	1000kg/2200 lb	

Email: