# **Activated alumina powder**

# **Products Introduction:**

Activated alumina powder is also known as the rho alumina powder, which is a alumina transition phase. Its main crystal phase is palumina base. Palumina is made by aluminum hydroxide through suspension roasting rapid dehydration and rapid cooling system.

Its specific surface area is more than 260  $m^2/g$ , so it has strong flexibility , water absorption performance, and certain hydration.

It replaces pure calcium aluminate cement in refractory castable binder, micro silicon powder and ultrafine alumina powder in adhesive and binder.

#### Characteristics:

IHigh surface area

ILow LOI

IHigh AL2O3

Item	Unit	Technical requirement
Particle size	um	10±0.5
ρ-AL <sub>2</sub> O <sub>3</sub>	%	≥65
AL <sub>2</sub> O <sub>3</sub>	%	92
SiO <sub>2</sub>	%	≤0.02
Fe <sub>2</sub> O <sub>3</sub>	%	≤0.02
Na <sub>2</sub> O	%	0.30-0.4
Surface area	m²/g	250-300
Pore Volume	ml/g	0.20-0.25
LOI	%	6-8

Note: We could manufacture activated alumina powder according to your required data.

#### Zibo XiangRun Environment Engineering Co., Itd

Phone:86-533-3037068 Fax: 86-533-3037068 Tel: 86-13518630890 13583393236

 $Website: \underline{Http://xradsorbent.com}; \ \underline{Http://www.aluminaadsorbents.com}$ 

international@xradsorbent.com; sales@aluminaadsorbents.com

Address: No.16, Hi-Tech Industrial Park, Development Zone, Zibo City, Shandong Province 255000, P. R. China

Email:

# Application:

It replaces pure calcium aluminate cement in refractory castable binder, micro silicon powder and ultrafine alumina powder in adhesive and binder.

### Storage:

lAvoid moisture, avoid scrolling, throw and sharp shocking during transportation, rainproof facilities should be readied..

Ilt should be stored in dry and ventilated warehouse to prevent contamination or moisture.

Package:25kg/plastic bag, 1000kg/jumbo bag

Туре	Super sack/Jumbo bag	
Powder	1000kg/ 2200 lb	

Email: